

Titanium Stick - 307954

Technical Data Sheet

Product Description

Titanium stick is a hand-mixable, titanium-reinforced epoxy putty stick specifically formulated to bond and repair materials that will be exposed to high temperatures in industrial maintenance applications. Each stick contains pre-measured portions of base and activator throughout. No measuring or mixing tools are needed - just cut, mix and apply.

When mixed to a uniform color, the materials combine to form a polymer compound that can be molded into shapes or used to build up, repair and patch almost anything. This industrial-strength product cures tough and hard and bonds tenaciously to metals. After 8 hours of cure, Titanium stick can be machined, tapped, drilled, ground or filed.

Titanium stick is solventless, low odour product with a long pot life, and has a service temperature of between -40 to +260°C.

Repair...

- Tanks
- Iron pipes
- Equipment
- Tools
- Ductwork

Rebuild...

- Stripped threads
- Blow holes
- Patterns
- Castings
- Molds

Note: Does not adhere to polyethylene, polypropylene or PTFE.

Mixing and application:

Before applying, roughen and clean the area to be repaired and then follow these easy steps. Wear impervious gloves when mixing or handling uncured product.

Twist or cut off required amount with gloved fingers, then mix by kneading to a uniform color. If mixing is difficult, warm Titanium stick to room temperature or slightly above.

Apply to the repair surface within 1 hour of mixing. Force into any cracks or holes to be filled and strike off excess material before hardening begins, preferably with a tool moistened with clean water. Heating Titanium stick or applying to warm surfaces will accelerate the cure. For a smooth cured appearance, rub with water or a damp cloth prior to hardening.

After 2 hours the epoxy will form a tenacious bond. Curing at higher temperatures (150°F/65°C) will provide a stronger bond and faster hardening; lower temperatures will retard the cure. After 8 hours at room temperature Titanium stick can be drilled, tapped, and sanded.

For best results: Use damp fingers for easier mixing, application, and a smooth appearance of the cured compound. Remove excess material before hardening begins.

Curing: Steel Stick has a work life of approximately 3-5 minutes. Functional cure occurs in 60 minutes.

Titanium Stick - 307954

Technical Data Sheet

Performance Data*		
Properties	Results	Test Methods
Uncured Properties		
Work life at 75°F (24°C)	1.5 to 2 hours	
Non-volatile content	>99%	
Density	16.5 lb/gal (1.90 g/cm ³)	
Functional cure (lap shear tensile strength=200 psi)	8 hours	
Cure time to full cure at 70°F (21°C)	3 days	
Cured Mechanical Properties		
Shore D hardness at 75°F (24°C)	80	ASTM D2240
at 500°F (260°C)	48	
Lap shear tensile strength (steel to steel) Cured at 75°F (24°C) for 24 hrs	250 lbs (2 MPa)	ASTM D1002
Cured at 150°F (65°C) for 24 hrs	750 lbs (5 MPa)	
High-temperature lap shear strength (steel to steel) Cured at 75°F (24°C) for 24 hrs + 500°F (260°C) for 1 hr.	250 lbs (2 MPa)	ASTM D1002
Compressive strength	8,000 psi (55 MPa)	ASTM D695
Shrinkage	<1%	ASTM D2566
High-temperature weight loss (24 hours)	<1% at 400°F (204°C) <2% at 500°F (260°C)	
Tg by DSC	134°F (57°C)	
Temperature limits Continuous	-40 to +450°F (-40 to +232°C)	
Intermittent	-40 to +500°F (-40 to +260°C)	
Chemical resistance	Resistant to hydrocarbons, ketones, esters, alcohols, halocarbons, aqueous salt solutions, and dilute acids and bases	
Cured Electrical Properties		
Electrical resistance	30,000 megohms-cm	ASTM D257
Dielectric strength	300 volts/mil	ASTM D149
<i>Typical properties are for information only, not for purposes of specification. The data above represents product performance in ideal laboratory conditions. Individual users' experience may vary depending on application conditions.</i>		

Health & Safety

- **Contains Epoxy Resin, Tri (dimethylaminomethyl) phenol, and Aliphatic Amines. Epoxies are skin/eye irritants and known sensitizers. Direct product contact may cause an allergic reaction in some individuals. Avoid skin/eye contact. Wear impermeable gloves when mixing or handling uncured product.**
 - **Inhalation of dust may be harmful. Avoid inhalation of dust. Wear dust mask and protective eyewear when sanding cured product.**
 - **Ingestion of product may be harmful. Avoid ingestion.**
 - **KEEP OUT OF REACH OF CHILDREN.**
- For additional health and safety information, consult a Safety Data Sheet.**

ISSUE No: 3

ISSUE DATE: March 2017

ISSUED BY: M.JOYCE

ITEM REF : 307907

PAGE 2 OF 2

